

# Survey Titanium Products

Product Grade	Gain on Ignition [%]	Ti Content Total [%]	Hydrogen Content [%]	Auto Ignition Temperature [°C]	Combustion Rate [sec/50cm]	Particle Size [µm]	Average Particle Size [µm]
Titanium hydride N	min. 58.4	min. 95	min. 3.8	> 400	not provided	99.9% < 63	5.0 ± 1.0
Titanium hydride P	min. 58.4	min. 95	min. 3.8	> 400	not provided	99.9% < 63	8.0 ± 2.0
Titanium hydride T	min. 58.0	min. 94.8	min. 3.8	not provided	not provided	99.9% < 63	3.5 ± 0.5
Titanium hydride U	min. 58.4	min. 95	min. 3.8	> 400	not provided	99.9% < 45	5.0 ± 1.0
Titanium hydride VM	min. 56.7	min. 94	min. 3.7	> 230	not provided	99.9% < 45	1.8 ± 0.2
Titanium hydride G	not provided	> 95	3.5 – 4.0	not provided	not provided	not provided	approx. 60
Ti metal powder E	57.0 ± 2.0	93.0 - 95.4	not provided	> 240	35 ± 10	99.9% < 45	3 ± 1
Ti metal powder A	56.0 ± 2.5	93.6 ± 1.5	not provided	> 200	30 ± 10	99.9% < 45	2 ± 1
Ti metal powder Q	min. 52	min. 91	not provided	not provided	30 ± 10	95% < 40	2.7 ± 0.3
Ti metal powder EP	63.5 ± 2.5	98.0 ± 1.5	not provided	not provided	17.5 ± 7.5	99.9% < 500	4.5 ± 1.5
Ti metal powder S 9.5	min. 64.5	min. 98.7	max. 0.1	> 400	35 ± 10	99.9% < 45	9.5 ± 1.5
Ti metal powder S 8	min. 64.5	min. 98.7	max. 0.1	not provided	35 ± 10	99.9% < 45	8 ± 1.5
Ti metal powder S <25	min. 64.5	min. 98.7	max. 0.1	not provided	37.5 ± 12.5	99.9% < 25	8.5 ± 1.5

On request Ti metal powder type S is available to meet government specification MIL-T-13405E, type I

Edition: May 2005

**Chemetall GmbH**

Special Metals Division

**Trakehner Straße 3  
D-60487 Frankfurt am Main  
P.O. Box 90 01 70  
D-60441 Frankfurt a.M.  
Phone +49 69 7165-3014  
Fax +49 69 7165-2523  
Mail [specialmetals@chemetall.com](mailto:specialmetals@chemetall.com)**

The above details have been compiled to the best of our knowledge on the basis of thorough tests and with regard to the current state of our long practical experience.  
No liabilities or guaranties deriving from or in connection with this leaflet can be imputed to us. Re-production in whole or in part, only for personal use.

